

Technical Data Sheet

EUROPLEX[®] SDX-F

Status: April 2010

The static dissipative polycarbonate sheet provides a permanent protection against electrostatic discharge events (ESD).

EUROPLEX[®] SDX-F sheets dissipate electric charges in a controlled way against earth. EUROPLEX[®] SDX-F is suitable for hot deformation.

<i>Product properties*</i>		<i>Value</i>	<i>Unit</i>	<i>Test method</i>
Electrical	Surface resistivity	10 ⁵⁻⁷	Ohm/sq	DIN IEC 60093
Physical	Density	1.20	g/cm ³	ISO 1183-1
Optical	Light transmission factor	85	%	DIN 5033, DIN 5036
	Light reflection factor	7	%	DIN 5033, DIN 5036
	Haze	1	%	ASTM D 1003
Mechanical	Tensile strength	60	MPa	ISO 527
	Modulus of elasticity	2400	MPa	ISO 527
	Yield stress	60	MPa	ISO 527
	Extensibility	6	%	ISO 527
	Nominal elongation	70	%	ISO 527
	Bending modulus	2100	MPa	ISO 178
	Bending strenght	100	MPa	ISO 178
	Bending stress at rupture	no rupture		ISO 178
	Bending stress at 3.5 %	80	MPa	ISO 178
	Edge fibre elongation at rupture	no rupture		ISO 178
	Edge fibre elongation at bending strenght	6	%	ISO 178
	Compression modulus of elasticity	2400	MPa	ISO 604
	Compression strength	70	MPa	ISO 604
	Nominal compression at compression strength	8	%	ISO 604
	Compression yield stress	70	MPa	ISO 604
Charpy impact strength	no rupture		ISO 179	
Charpy notched bar impact strength	11	kJ/m ²	ISO 179	
Thermal	Vicat softening point	145	°C	ISO 306
	Thermal expansion coefficient	7 x 10 ⁻⁵	1/K	ASTM D 696

* All data are related to sheets with 3 mm thickness.

Legal advice

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. (april 2008)

Contact: Evonik Degussa GmbH
Creavis Technologies & Innovation

Elke Nelles-Schwelm
Phone +49 2365 49-5966
elke.nelles-schwelm@evonik.com